

ATMOSPHERE

RUNWAY 2



TO MARKET

PRODUCT SPECIFICATION

| | |
|----------------------------|--|
| Product Line | Citation, Phenon, Falcon, Gulfstream, Global |
| Composition | Through-Body Color Tiles - 100% Post-Consumer Recycled Tire Rubber SBR (Styrene-Butadiene Rubber) + 100% Post-Industrial Colored EPDM (Ethylene-Propylene Diene Monomer) 2019 To Market Global proprietary combinations - AFTA Registered 2005 |
| Installation | Straight Edge Tile / Rolls - Glue down Interlocking Tile - Loose Lay |
| Size | Straight Edge Tile - 23" x 23" Interlocking Tile - 21.75" x 21.75" Rolls - 4' x 25' or 4' x 50' |
| Thickness | Straight Edge Tile / Rolls - 4 or 9mm Interlocking Tile - 9mm |
| Certifications | FloorScore®; ISO-9001 / ISO-14001 |
| Warranty | 10-Year Commercial |
| Abrasion & Wear Resistance | ASTM-D3390-05 / ASTM C501 - 0.73 g/loss |
| Accelerated Traffic | ASTM-D6119-05 - Performance indicator 5 (no change) |
| Acoustic Rating | ASTM-E989-06 / E492-96 4mm-IIC-57 / 9mm - IIC-59 (Impact Sound Transmission / Impact Insulation) |
| Chemical Resistance | ASTM-F925-97 - no change (surface dulling, staining attack, color change) |
| Coefficient of Friction | ASTM-D2047 - .85 dry / 1.01 wet |
| Compression | ASTM-D395-03 - 9.70% (compression set under constant force) |
| Critical Radiant Flux | ASTM-E648 - Class 1 / Class 2 |

| | |
|---------------------------|--|
| Density (PCF) | ASTM-D3676 - 07 - 66 lbs / cubic foot |
| Elongation at break | ASTM-D412 - 06ae2 / 120% |
| Chemical/Stain Resistance | ASTM-F925 No Change (ammonia, bleach, rust, grass, coffee, fruit juice, cola, ink, lipstick) |
| Custom | Custom colors, logo or graphic designs available |
| Country of Manufacture | Made in the USA |

For additional information + product samples, please contact To Market Global.